

Gates Black Gold® Sour Service

5,000 psi W.P. - 10,000 psi Test



Specification 4774F





OFFSHORE

I AND RIG

Certification/Standards

ABS (Additional Cost)

Coupling/Mat'l Traceability (Additional Cost)

DIN German (Additional Cost)

DNV (Additional Cost)

Health & Safety Executive (Additional Cost) Letter of Conformance (Additional Cost)

NACE

Test Certificates

RECOMMENDED FOR: Flexible connection between the standpipe and swivel (rotary drilling) or between pump

and standpipe (rotary vibrator).

TEMPERATURE: -40°F to +200°F (-40°C to +93°C).

TUBE: Type V (Fluoroelastomer). Black. Resists abrasion, corrosion, oil, weather and up to

20% H₂S. NOTE: Hose is manufactured to handle up to 20% Hydrogen Sulfide (H₂S) for

1 hour at 93°C (200°F) at rated working pressure.

REINFORCEMENT: Multiple layers of "close wound", high tensile steel cables with one layer of adhesion

fabric placed between cable layers. Multiple layers of reinforcement under cover.

COVER: Type C₄ (Modified Nitrile). Black. Specially compounded UltraBrasion cover is resistant

to abrasion, corrosion, cutting, gouging, oil and weather. One continuous longitudinal

yellow transfer label. Serial number and manufacture date embossed.

COUPLINGS: Swaged – meets NACE MR0175. API does not recommend use of pipe threads for

working pressures of 5000 psi and above. Couplings can be supplied with your choice of end fitting (see "Most Commonly used Welded-On Fittings" section for more detailed information). **NOTE:** FIELD WELDING OF FITTINGS TO COUPLING IS **NOT**

RECOMMENDED.

FITTINGS: Hammer Unions

Hubs

Flanges













Female Sub

Male Sub./Nut

Available Sizes (Inches)	2-1/2	3	3-1/2	4	Spec.
Nom. O.D.	4.15	4.61	5.25	5.58	4774F
Min. Bend Radius (Inches)	36	48	54	54	
Wt. per Ft. of hose (Lbs	10.1	11.1	13.2	13.9	
Swage Cplg. Wts. Each (Lbs)	33	44.5	47	55	All Control
Maximum length of hose (Feet)	90	90	90	90	

OPTIONAL:

AVAILABLE SIZES:

Accessories such as SAFETY CLAMPS, HOSE LIFT EYE & COLLAR CLAMP and STAINLESS STEEL ARMOR are found on page 53.